



COHERETM PLASTOMER 8570D

METALLOCENE POLYOLEFIN PLASTOMER

DESCRIPTION

COHERETM Metallocene Polyolefin Plastomer (POP) 8570D is an ethylene-octene copolymer produced via solution polymerization using metallocene catalyst. It can be used in monolayer or coextruded film to enhance heat-sealing properties, clarity, toughness, flexibility and elasticity. It has strict gel control to meet high quality film requirements.

TYPICAL APPLICATIONS

- Sealant layer in multi-layer film;
- Cling layer in stretch wrap film;
- Adhesive layer in surface protect film.

TYPICAL PROPERTY VALUES

Revision 20231031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	5.0	g/10 min	ASTM D1238
Density			
at 23°C	0.868	g/cm ³	ASTM D792
FORMULATION			
Anticaking	<input checked="" type="checkbox"/>	-	Internal method
MECHANICAL PROPERTIES			
Flexural Modulus (1% Secant)	10.8	MPa	ASTM D790 A
Tear Strength (Type C)	35.3	kN/m	ASTM D624
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
stress at break	6	MPa	ASTM D638
elongation at break	1100	%	ASTM D638
100% modulus	2.3	MPa	ASTM D638
THERMAL PROPERTIES			
Melting Point	62	°C	SABIC method

(1) All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.

FOOD REGULATION

Please contact the local Sales / Technical representative for details.



STORAGE AND HANDLING

POE Polyolefin Elastomer resins (in pelletized form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 30 °C. Further avoid temperatures above 50 °C and below 10 °C. Please mind the temperature conditions when using the low density grades <0.875 g/cm³, especially when the shipment or storage temperature would approach the softening and melting temperature of the POE resin. Outer package wrap should not be removed from the pellets until the products are ready to be used. Stacking of pallets is not recommended due to dimensional instability and material blocking risk. Grades with D suffix are being treated with anti-caking dust agent to reduce blocking behaviour. It is advisable to process Polyolefin Elastomers resins within 6 months after delivery, this because also excessive aging can lead to a deterioration in quality.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.