



SABIC® EPS 552

EXPANDABLE POLYSTYRENE

DESCRIPTION

Standard expanded Polystyrene SABIC® EPS552 is manufactured by the suspension polymerization of styrene monomer. The polymerization is generally carried out in a batch process. SABIC® EPS552 is supplied in free flowing beads, containing pentane (CFC free) as a foaming agent. It is used for fast cycle low density block molding applications with good surface finish.

TYPICAL APPLICATIONS

SABIC® EPS552 is a standard fast cycle grade used for shape molding with wall thickness greater than 10mm and medium to high density block molding.

TYPICAL PROPERTY VALUES

Revision 20181219

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
TYPICAL DATA			
Bead Distribution	0.6 – 1.1	mm	SABIC 020
Minimum Density (1)	17	kg/m³	SABIC 027
Normal Density Range	17 – 30	kg/m³	SABIC 027

⁽¹⁾ One pre-expansion, lower density can be achieved by multiple pre-expansions

PROCESSING CONDITIONS

SABIC® EPS552 is processed in three steps:

Pre-expansion, Maturation and Molding

SABIC® EPS552 is heated by steam at 100°C in a pre-expander. The foaming agent present in the polystyrene beads vaporizes and mixes with steam. The gas mixture so produced subsequently softens the beads and expands them to 30-40 times to its initial size. In maturation process the foaming agent and steam condense in the cells of the pre-foamed beads causing partial vacuum, which is compensated by the diffusion of air into the beads. The maturation period could be between 3 and 24 hours. In the molding process the matured pre-foamed beads can further be processed by direct steam to the desired shape molding

FOOD REGULATION

SABIC® EPS552 is suitable for food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

STORAGE AND HANDLING

SABIC® EPS552 is supplied in 1 MT semi bulk cardboard containers (octabins).

SABIC® EPS552 contains flammable foaming agent, pentane, which can form explosive mixture with air. Hence, expandable polystyrene should be stored in closed containers below 25°C. Storage and processing areas should be adequately ventilated. Source of ignition like smoking, sparks, welding and naked flame should be strictly avoided. Should fire occur, the processor should use dry powder or carbon dioxide extinguishers, particularly in the area of hot wire cutting machines.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.