



# SABIC® HDPE B5206

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

HDPE B5206 is high density polyethylene specially developed for large blow molding / Jerry cans. The material offers high stiffness, good processability and excellent combination of stiffness/ESCR.

### TYPICAL APPLICATIONS

B5206 is specially designed for Standard jerry cans, UN approved jerry cans and standard drums up to 60L The grade is intended for food contact application.

### TYPICAL PROPERTY VALUES

Revision 20211207

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 21.6 kg load <sup>(1)</sup>	6.5	g / 10 min	ISO 1133
<b>Density at 23°C</b>	952	kg / m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile modulus <sup>(2)</sup></b>	1050	MPa	ASTM D638
<b>Tensile Strength at Yield</b>	26	MPa	ASTM D638
<b>Tensile Strain at Yield</b>	10	%	ISO 527-1 / -2
<b>Charpy Notched Impact Strength (-30°C, Type 1, Notch A)</b>	36	kJ / m <sup>2</sup>	ISO 179
<b>FNCT (3.5 MPa, 2 % Igepal BC/9, 80°C)</b>	50	Hrs	ISO 16770

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

### PROCESSING CONDITIONS

Recommended processing temperature 180-220°C

### STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.